

## Plank Fineline

## 14 mm Click

| Technical information                                  |  |
|--|--|
| Produced according to:                                 | European parquet norm EN 13489 - 2017  |
| Dimension:   | 14 x 138 x 2200 mm   |
| Toplayer:  | about 3.5 mm   |
| Construction:  | 3-layer construction; Hardwood toplayer,<br>middlelayer and bottomlayer made of<br>spruce<br>Toplayer about 3.5 mm<br>Middlelayer 8.8 mm<br>Bottomlayer 1.7 mm |
| Boards/ m² per carton:                                 | 10/ 3.04   |
| Cartons/ m² per pallet:                                | 42/127.68  |
| Slotted top layers per carton/<br>minimum length (mm): | -  |
| Weight per carton/ pallet in kg:                       | 25.5/ 1071   |
| Floor heating systems:                                 | Well suitable to very well suitable  |
| Fire behavior <sup>1)</sup> :                          | Cfl-s1 and Dfl-s1 depending on wood specie and surface treatment   |
| Content of formaldehyd 2):                             | El   |
| Content of pentachlorphenol (PCP) 2):                  | no performance detected  |
| Density kg/ m³ <sup>2)</sup> :                         | about 600  |
| Antislip performance:                                  | Live Satin USRV 25 <sup>2)</sup> Live Matt USRV 29 <sup>2)</sup> Live Natural USRV 40 <sup>2)</sup>  |
| Abrasion resistance:                                   | Live Satin 70/1100 <sup>3)</sup><br>Live Satin 100 <sup>4)</sup>   |
| Thermal condactivity 2):                               | 0.15 W/ (m·K)  |
| Areal thermal resistance 5):                           | 0.093 m <sup>2</sup> · K/ W  |





DOP 4658







<sup>1)</sup> according to DIN EN 13501-1,  $^{2)}$  according to DIN 14342,  $^{3)}$  according to ENV 13696,

 $<sup>^{4)}</sup>$  according to DIN 68861,  $^{5)}$  according to EN 12524